



Yihe Core

DESCRIPTION

- Core materials and resin flow medium for closed mould processes, including infusion and RTM.
- Pressure-stable polyester non-woven fabrics and compatible with all regular types of resins, including unsaturated polyester, vinyl ester, phenolic and Epoxy.

APPLICATIONS

- Marine: Yacht and boat hulls, decks and structural components
- Transportation: interior and exterior parts of cars, trailers, trucks, RV, buses and trains
- Leisure: kayaks, surfboards, swimming pool
- Industrial: furniture , exterior wall panels of buildings, fans, pressure vessels, storage tanks, artificial stones
- Wind energy: nacelle covers and blades



ADVANTAGES

- A cost-effective core material
- Hexagonal closed-cell structure exhibits high compression resistance and enables weight reduction
- Improve parts appearance
- Superior conformability
- Improvement of impact resistance and stiffness
- Fast resin flow along channels between hexagons
- Available in max.10mm thickness

BASIC PROPERTIES

Properties		PM1.5	PM2	PM3	PM4	PM5	PM6
Thickness	mm	1.5	2.0	3.0	4.0	5.0	6.0
Thickness loss at 0,8bar	%	<8	<8	<8	<8	<8	<8
Roll length	m	100	80	50	40	30	25
Roll width	m	1.27	1.27	1.27	1.27	1.27	1.27
Max processing temperature	°C	180	180	180	180	180	180
Dry weight	g/m ²	100	140	180	240	310	340
Resin uptake	kg/m ² /mm	0.4-0.5					
Density impregnated	kg/m ³	500-600					

MECHANICAL PROPERTIES OF PM3 (AFTER IMPREGNATED WITH UNSATURATED POLYESTER RESIN)

Mechanical properties	Unit	Value	Test Method
Flexural strength	MPa	8.5	ASTM D790
Flexural modules	MPa	900	ASTM D790
Tensile strength across layers	MPa	4	ASTM C297
Compression strength:10% strain	MPa	8.5	ISO 844
Shear strength	MPa	4	ASTM C273-61
Shear modules	MPa	45	ASTM C273-61

TDS version: V3 05 2026

Notes:

The information contained in this document is compiled by Suzhou Yihe New Material Co., Ltd. in good faith. However, the company makes no representations or warranties regarding the accuracy or completeness of the (technical) information provided herein. Suzhou Yihe New Material Co., Ltd. shall not be held liable for any damages caused by any (printing) errors or omissions. The company reserves the right to make changes to the content without prior notice.