

# PT Technical Data Sheet



## Yihe Core

### DESCRIPTION

- Core materials and resin flow medium for closed mould processes, including infusion and RTM.
- Pressure-stable polyester non-woven fabrics and compatible with all regular types of resins, including unsaturated polyester, vinyl ester, phenolic and Epoxy.

### APPLICATIONS

- Marine: Yacht and boat hulls, decks and structural components
- Transportation: interior and exterior parts of cars, trailers, trucks, RV, buses and trains
- Leisure: kayaks, surfboards, swimming pool
- Industrial: furniture, exterior wall panels of buildings, fans, pressure vessels, storage tanks, artificial stones
- Wind energy: nacelle covers and blades



### ADVANTAGES

- A cost-effective core material
- An efficient print blocker
- The dot-like structure exhibits high compression resistance and enables weight reduction
- Improve parts appearance
- Superior conformability
- Improvement of impact resistance and stiffness
- Available in max. 3mm thickness

### BASIC PROPERTIES

Properties		PT1.5	PT2	PT3
Thickness	mm	1.5	2.0	3.0
Thickness loss at 0,8bar	%	<20	<20	<20
Roll length	m	120	80	50
Roll width	m	1.27	1.27	1.27
Max processing temperature	°C	180	180	180
Dry weight	g/m <sup>2</sup>	100	120	150
Resin uptake	kg/m <sup>2</sup> /mm	0.4-0.6		
Density impregnated	kg/m <sup>3</sup>	600-800		

### MECHANICAL PROPERTIES OF PT2 (AFTER IMPREGNATED WITH UNSATURATED POLYESTER RESIN)

Mechanical properties	Unit	Value	Test Method
Flexural strength	Mpa	20	ASTM D790
Flexural modules	Mpa	1800	ASTM D790
Tensile strength across layers	Mpa	8	ASTM C297
Compression strength:10%strain	Mpa	4	ISO 844
Shear strength	Mpa	8	ASTM C273-61
Shear modules	Mpa	40	ASTM C273-61

TDS version: V3 05 2026

#### Notes:

The information contained in this document is compiled by Suzhou Yihe New Material Co., Ltd. in good faith. However, the company makes no representations or warranties regarding the accuracy or completeness of the (technical) information provided herein. Suzhou Yihe New Material Co., Ltd. shall not be held liable for any damages caused by any (printing) errors or omissions. The company reserves the right to make changes to the content without prior notice.